

DATA SHEET

Filter media

Dura-Life® Anti-Static

Dura-Life® Anti-Static

| Appearance | Grey |
|---|--|
| Use | Filter bags |
| Composition | Mixture of polyester fibres, bicomponent polyester and epitropic conductive fibres |
| Area weight | 320 g/m ² |
| Thickness | 1.6 mm |
| Air Permeability (Frazier) | 750 m³/m²/h at 125 Pa |
| Dimensional stability at 177 °C (%) | <3.0% |
| Surface finish | None |
| Additional treatments | Heat set |
| Surface electrical resistance (DIN 54345) | Less than $10^8\Omega$ |
| IFA/BIA certificate (DIN 660335-2-69) | N/A |
| Temperature (dry heat) | |
| Continuous | 135 °C |
| Peaks | 150 °C |
| Chemical resistance | |
| Hydrolysis | Poor |
| Acids | Good |
| Alkalis | Good |
| Oxidising agents | Very good |
| Organic solvents | Very good |
| Abrasion resistance | Very good |
| Supports combustion | Yes |
| Application field | The antistatic conductive fibre content prevents the build up of any dangerous static charges on the media surface, which could initiate an explosion inside the collector casing. Also, with certain dusts, these charges can have an effect on the dust release properties of the media, thereby influencing filter performance. |