



DATA SHEET

Filter media
Polyester Anti-Static

Polyester Anti-Static

Appearance	Grey
Use	Pleatable filter media
Composition	100% Polyester Spunbonded
Area weight (g/m²)	270
Thickness (mm)	0.63
Air Permeability (m³/m²/h - 200 PA)	670
Surface electrical resistance (Ohm)	$\rho < 10^3 \Omega$
IFA/BIA certificate (DIN EN 60335-2-69:2008)	M
Max. working temperature (C°)	150
Volume of pores (%)	68
Application field	Paper, powder painting, aluminium, toner, sugar, pigments, pvc, zinc, titanium, graphite, meal, tobacco, arc plasma, ceramic painting powder, plastic material processing, resin, epoxy material, metal coating.